



# DECO GUARD™ PLUS 350VOC

siloxane modified methyl methacrylate

[www.SouthernStainAndSeal.com/Deco-Guard](http://www.SouthernStainAndSeal.com/Deco-Guard)



Deco Guard™ Plus is a non-yellowing, high gloss, siloxane modified methyl methacrylate with excellent adhesion to properly prepared concrete substrates. Deco Guard™ Plus's unique chemical reactive formulation provides superior resistance to de-icing road salts, salt water pool systems, rain, sleet and snow compared to standard sealers used to protect exterior concrete.

### Key Features & Typical Benefits

- Minimizes damage due to water and salt water from de-icing road salts and salt water pool systems.
- Excellent penetration and adhesion to clean, unsealed new or old concrete.
- Non-Yellowing tough Siloxane Methyl Methacrylate.
- Can be applied as a reseat on certain SurfKoat brand solvent based acrylic sealers or equivalent (test for compatibility first).
- VOC compliant for most areas in the United States and Canada.

### Recommended Applications

- Effective on applications such as...
- Concrete Pool Decks
  - Stamped & Stenciled Concrete
  - Acid Stained Concrete
  - Overlaid/Microtopped Concrete
  - Exposed Aggregate Concrete
  - Smooth Trowel Concrete
  - Broom Finish Concrete
  - Most other new or existing concrete surfaces where water and salt damaged resistance is required.



### Specifications / Compliances

- ASTM C-1315, Type 1, Class A & B
- Dried coating is USDA accepted
- Meets OTC-Phase I, CARB-2002, Maricopa CTY AZ and LADCO VOC restrictions.

### Typical Properties & Technical Information

PROPERTY	VALUE
Solids/Active Content, Percentage by weight	25% +/- 1%
Dry Time - Tack Free	30 minutes - 1 hour
Dry Time - Foot Traffic	4 hours - 6 hours
Dry Time - Heavy Traffic	24 hours - 48 hours
Re-Coat Time Window	4 hours - 24 hours
Application Temperature	50° F - 80° F
VOC (Volatile Organic Compound) Content	Less than 350 grams/Liter
Appearance - Wet	Clear
Appearance - Dry	Clear and High Gloss

Information above is based on lab temperatures of 70° - 72°F at 50% RH. Using this product outside these conditions may affect the accuracy of the information above. Always test prior to use. For professional use only. Do not thin.

Surface Koatings, Inc.  
134 Davis St. • Portland, TN 37148  
P: (615) 323-9461 • F: (615) 323-9816

Refer to technical data and SDS prior to use.

# DECO GUARD PLUS 350VOC

## Application Instructions

**SURFACE PREP:** Concrete surface must be clean and free of all contaminants and water. Do not apply if rain is forecast within 24 hours. If moisture is present or if the surface is not clean and free of all contaminants, the sealer may have white spots and have premature delamination and failure. May be applied when damp (not "wet") to freshly placed concrete surfaces as a cure & seal. Horizontal surfaces must be finished and show no "sheen" from bleed water.

Substrate and air temperature must be no less than 40° F and not exceed 80° F. If applied outside these limits the sealer may not achieve adequate film formation and may have excessive air entrapment, bubbles, blushing or hazing. Note that in direct sunlight, substrate temperature can exceed 150° F which can cause extreme bubbling issues. If possible always apply as concrete is cooling, rather than as concrete is warming. Warming by the sun causes the air inside the concrete to expand and push out through the surface, often causing bubbles in the still wet sealer. Low VOC solvent based sealers dry faster than traditional 700 VOC sealers. Apply on cool, overcast days to avoid issues. Do not apply if the temperature is expected to achieve 85° F or higher. For Professional use only. Do not thin.

**MIXING:** Stir well before using. Material may separate during long term storage.

**COVERAGE RATE:** First Coat : 200 - 300 ft<sup>2</sup> per gallon\*      Optional Second Coat : 300 - 400 ft<sup>2</sup> per gallon\*

\*Coverage rates may vary depending upon surface porosity, texture, application method and prior sealer application. Excessive build up should be avoided.

**APPLICATION:** Apply using an 3/8" long nap roller cover using long even uniform strokes at approximately 200-400 square feet per gallon depending job requirements, porosity and texture of substrate. An airless sprayer containing a .519 tip size may be used as well. Thick or puddle areas may prevent the solvent from evaporating and may be susceptible to moisture intrusion which may cause milky white spots. Applying too thin may cause sealer to prematurely delaminate, flake or wear away. Allow sealer to dry for 24 hours for light traffic and at least 48 hours for heavy traffic. If applying two coats, wait approximately 4 – 6 hours between coats. **FOR PERSONAL PROTECTION USE GLOVES, GOGGLES, AND RESPIRATORS.**

When using as a cure & seal, apply only one coat to meet specifications. Extreme bubbling and/or hazing may occur due to lack of permeability.

**PLEASE NOTE:** It is always recommended to test the product in a small, inconspicuous area (on the same concrete substrate) for desired results prior to application. Coverage rates may vary for all coatings and substrates depending on porosity, density, texture etc. When applying, do not exceed 400 sq. ft. per gallon. Applying too thin of a coating may cause inadequate film formation or performance expectations may be limited. **DO NOT USE ON BRICK.**

---

## Precautions and Limitations

- This product will not freeze during storage, however, allow temperature to rise to 50°F prior to application.
- All HVAC ventilation ducts should be somehow blocked prior to application so solvent fumes are not distributed.
- If using indoor, use proper ventilation while applying and for hours after application to ensure fumes are removed.
- It is not recommended to apply product over carpet, tile, or other types of floor adhesives.
- This product performs best when applied as one or two medium-light coats, not one heavy coat.
- Please be aware that this product when cured may be slippery when wet. An anti-slip additive, such as Surf-Grip, can be added to reduce slip hazards.
- This product is not resistant to brake fluid, gasoline, and many similar products.
- It is not recommended to thin product. Improper thinning may cause sealer to delaminate in a short time frame.
- This product may darken the surface of many new and existing concrete slabs. Test prior to use.
- **SOLVENT VAPORS ARE HEAVIER THAN AIR AND MAY TRAVEL ALONG THE GROUND OR MAY BE MOVED BY VENTILATION AND IGNITED BY PILOT LIGHTS, OTHER FLAMES, SPARKS, HEATERS, SMOKING, ELECTRIC MOTORS, STATIC DISCHARGE, OR OTHER IGNITION SOURCES AT LOCATIONS DISTANT FROM MATERIAL HANDLING POINT.**

---

**CLEAN-UP:** Use xylene. Dispose of containers in accordance with local, state and federal regulations.

**PRODUCT REMOVAL:** Dried, cured sealer may be removed with a commercial paint stripper, such as Nock-Off or by using a diamond grinding method, sandblasting method or similar mechanical action.

**SHELF LIFE:** Up to one year from manufacture date in its original, unopened container stored at room temperature.

**PACKAGING:** Available in 1 gallon, 5 gallon and 55 gallon containers.

Always read all technical information, label and SDS prior to use. This information can be found online or by calling customer service at the number below.