



AQUALON™ L-100

lithium silicate concrete densifier

www.SouthernStainAndSeal.com/Aqualon-L-100



Aqualon L-100 is an environmentally friendly, VOC free, lithium silicate concrete floor densifier, hardener, and sealer. Aqualon L-100 is designed to penetrate untreated, bare concrete surfaces providing a permanent glossy, dust proof floor. Aqualon L-100 reacts quickly with the floor surface to produce initial and ultimate hardness. Aqualon L-100 shows great effectiveness when used in conjunction with a floor polishing machine, yielding a highly protected, hardened, and densified floor.

Key Features & Typical Benefits

- Effective on new and old concrete surfaces and very easy to maintain. Combats surface ASR.
- A safer floor surface. Provides excellent non-slip, high traction properties.
- Yields a UV stable, superior sheen, and resistance to abrasion and scuffing.
- Non-flammable and odorless formula for easy indoor use.
- Contains 0 g/L VOC content making this product legal for sale to all regions of the US and Canada.

Recommended Applications

- Effective on applications such as...
- Polishing Systems
 - Broom Finished
 - Troweled Concrete
 - Burnished Concrete
 - Many other concrete floor applications where a floor densifier is specified.



Specifications / Compliances

- Meets OTC, CARB, LADCO & SCAQMD VOC restrictions.

Typical Properties & Technical Information

PROPERTY	VALUE
Solids/Active Content, Percentage by weight	15% +/- 1%
Dry Time - Tack Free	1 - 2 hours
Dry Time - Foot Traffic	12 - 24 hours
Dry Time - Heavy Traffic	24 - 48 hours
Re-Coat Time Window	2 - 3 hours
Application Temperature	50° F - 80° F
VOC (Volatile Organic Compound) Content	0 grams/Liter
Appearance - Wet	Clear (May show slight haze)
Appearance - Dry	Crystal Clear

Testing in accordance with procedures outlined in EPA Method 24, "Volatile Organic Content VOC of Paints and Related Coatings". The solids content was determined in accordance with ASTM D 5095 and the VOC was calculated in accordance with ASTM D 3960.

Surface Koatings, Inc.
134 Davis St. • Portland, TN 37148
P: (615) 323-9461 • F: (615) 323-9816

Aqualon L-100

Application Instructions

SURFACE PREP: Protect all people, property, and plants not to be treated with Aqualon L-100 as product splash and wind drift could occur.

Do not apply to any surface that is dirty, frozen, or heavily saturated or flooded with water. Surface must be clean and free of all debris, dry, and absorbent. Mist water in a small area to test the surface for absorbency. Any surface to be treated should uniformly wet out. If the surface to be treated does not wet out uniformly, it is then recommended to prepare the surface mechanically to remove any remaining surface contaminants.

Substrate temperature must be no less than 40 degrees F and not exceed 80 degrees F.

MIXING: No mixing is necessary prior to application.

COVERAGE RATE:	First Coat	Second Coat
Freshly placed, uncured, troweled concrete	800-1000 ft ² per gallon*	800-1000 ft ² per gallon*
Cured, troweled concrete	600-800 ft ² per gallon*	600-800 ft ² per gallon*
Cured, ground concrete	400-800 ft ² per gallon*	400-800 ft ² per gallon*

*Coverage rates vary depending upon surface porosity, texture, and application method.

APPLICATION:

New (Uncured) Concrete: It is not traditionally recommended to apply Aqualon L-100 to concrete earlier than 28 days. If this application is necessary, ensure the removal of all soft cut saw debris prior to application. Apply after final troweling at a rate of 800-1,000 sq. ft. per gallon using an industrial grade sprayer with a 0.5 gal./min. fan tip, lint free mop, or soft bristle push broom. Ensure floor saturation for 15-20 minutes, removing any puddle areas with a soft bristle push broom or mop. Apply more Aqualon L-100 to areas that appear to be more porous and are absorbing the material more. Rework any excess material with a soft bristle broom as to allow the material to dry evenly. Remove any excess or residue with a stiff bristle broom or dry pad floor buffer.

Existing Concrete: Apply at a rate of 600-800 sq. ft. per gallon using an industrial grade sprayer with a 0.5 gal./min. fan tip, lint free mop, or soft bristle push broom. Ensure floor saturation for 15-20 minutes, removing any puddle areas with a soft bristle push broom. Apply more Aqualon L-100 to areas that appear to be more porous and are absorbing the material more. Rework any excess material with a soft bristle broom as to allow the material to dry evenly. Remove any excess or residue with a stiff bristle broom or dry pad floor buffer.

Polished Concrete: After completing the 400 grit stage of polishing, apply a saturating, uniform coat of Aqualon L-100 at a rate of 400-600 sq. ft. per gallon using an industrial grade sprayer with a 0.5 gal./min. fan tip, lint free mop, or soft bristle push broom, ensuring floor saturation for 15-20 minutes. Do not allow to puddle. Allow to dry. Follow through with additional polishing steps until desired appearance is achieved. Additional applications of Aqualon L-100 can be added at any stage before the final polishing phase is done if necessary at a rate of 600-800 sq. ft. per gallon. Allow to dry. Remove any excess residue with polishing diamonds or polishing pads. Flushing with water is not necessary. Note: For softer concrete an initial application of Aqualon L-100 can be applied after the 80 grit stage prior to the standard polishing steps to achieve a harder surface.

PLEASE NOTE: It is always recommended to test the product in a small, inconspicuous area (on the same concrete substrate) for desired results prior to application. Coverage rates may vary for all liquids/coatings and substrates depending on porosity, density, texture etc. If applying by spray method, extended coverage rates may be achieved.

Precautions and Limitations

- This product will freeze during storage. Store at temperatures above 40°F.
- All HVAC ventilation ducts should be somehow blocked prior to application so fumes are not distributed.
- Do not puddle or apply in thick coats. This product should be applied only as explained above.
- This product is harmful if swallowed. Abide by recommended safety guidelines.
- This product is not a curing compound. Use on concrete less than 3 days old may result in a reduction of effectiveness.
- This product was designed for exterior as well as interior decorative concrete.
- It is not recommended to thin product.
- It is recommended to test this product prior to using on entire application.
- The use of high alkaline or acidic cleaners on the treated surface is not recommended and can be damaging.
- Protect metal, glass, wood, brick, and painted surfaces. Wash immediately with clean water if contact occurs.

CLEAN-UP: Use soap and water. Dispose of containers in accordance with local, state and federal regulations.

PRODUCT REMOVAL: Attempted removal of this product is not recommended.

SHELF LIFE: Up to one year from manufacture date in its original, unopened container stored at room temperature.

PACKAGING: Available in 1 gallon, 5 gallon and 55 gallon containers.

Always read all technical information, label and SDS prior to use. This information can be found online or by calling customer service at the number below.